

EVERBUILD 704 POWDER WALL TILE GROUT- BOX

Colour	Product Code	Pack Size	Box Qty
White	GROUT1	1KG	10

Product Description

EVERBUILD POWDERED WALL TILE GROUT is a cement based powdered grouting compound with added PVA to promote adhesion. Simply mix with water to give a pure white paste. Can be used on wall joints up to 3mm. Suitable for use in kitchens, bathrooms and shower areas. May be used internally and externally.

Benefits

- Excellent water resistance.
- Dries brilliant white.
- Compressible.
- Resists mould growth.
- Fine fillers present will not scratch glazed tiles.
- Interior/exterior use.
- Extended open time - large quantities may be mixed for covering large areas.

Areas For Use

- Grouting wall tiles on most surfaces up to 3mm joint width
- Recommended for grouting domestic, communal and power shower areas.
- Suitable for constant immersion; e.g. in swimming pool walls
- Suitable for use with ceramic, quarry and natural stone tiles and mosaics.
- Coloured grouts may be made by adding up to 5% by weight of EVERBUILD POWDER MORTAR TONE.
- May be used on floors when mixed with EVERBUILD SBR (1:1 dilution with water)

Limitations

- Always mix with clean fresh water.
- Allow adhesive to dry thoroughly before grouting (24hrs on porous, up to 5 days on non-porous surfaces). This prevents staining..
- Protect from running water and frost until completely dry.
- Do not use where application would trap moisture within the substrate.
- If joints are wider than 3mm, use EVERBUILD SBR as an admixture diluted 1:1 with water (will increase width up to 15mm max).
- Never add further water once the grout has been mixed. This will destroy the strength.
- Allow 3 days after grouting before using shower areas.

Surface Preparation

Ensure that the area to be grouted is clean, dry and free from loose adhesive before grouting.
ALWAYS CHECK THAT THE ADHESIVE IS DRY BEFORE COMMENCING.

TILING SAND/CEMENT RENDER/SCREED/PLASTER/PLASTERBOARD

Mix grout with water as detailed below. Leave at least 24 hours before grouting., except when using EVERBUILD RAPID SET, where grouting may be carried out 2-4 hours after fixing, depending on temperature.

TILING IMPERVIOUS SURFACES(ASPHALT/EXISTING TILING ETC)

Mix grout with water and leave at 5 days before grouting, except when using EVERBUILD RAPID SET, where grouting may be carried out 2-4 hours after fixing, depending on temperature

TILING SURFACES SUBJECT TO MOVEMENT (WOOD ETC)

Mix grout with EVERBUILD SBR diluted 1:1 with water. Leave at least 24 hours before grouting, except when using EVERBUILD RAPID SET, where grouting may be carried out 2-4 hours after fixing, depending on temperature.

TILING IN AREAS SUBJECT TO INTERMITTENT/CONSTANT WATER IMMERSION

Mix grout with EVERBUILD SBR diluted 1:1 with water. Leave at least 24 hours before grouting. Except when using EVERBUILD RAPID SET, where grouting may be carried out 2-4 hours after fixing, depending on temperature. Swimming pools should not be filled for at least three weeks after grouting.

Application

All surfaces should be clean, dry and free of dust and loose adhesive before commencing. Refer to directions for specific surfaces and related mix designs.

Tile must be left for at least 24hr (5 days on non-porous surfaces) for the adhesive to dry before grouting. Mix approximately 2 parts powder to 1 part water. Mix to a smooth slump free paste. Allow to stand 10 minutes before grouting, and then re-stir.

Apply by cloth or squeegee. Push grout well into joints so no voids remain behind. Remove excess grout with a damp cloth before it dries.

Protect all grouted areas from running water and frost until the grout is completely dry.

Specific Data

Appearance	Fine White Powder
SG at 20°C	1.8gcm ³ (approx)
Application Temp	5°C to 35°C
Service Temp	-30 to 100°C.
Open Time	1 hour @20°C
Bed Thickness	6mm (use SBR admix for joints 6mm-12mm)
Setting Time	3 - 4 hours (hard in 24 hours)
Storage	Store at moderate temperatures. PROTECT FROM DAMP
Coverage	This grout will cover at a rate of 1.5kg per 6 sq. meters of 150 x 150 tiles with a joint width of 2mm. This will vary according to tile size and joint width.

Health & Safety

Consult MSDS for full list of hazards.

Storage

Store at moderate temperatures. PROTECT FROM DAMP.

Shelf Life

Minimum 12 months when stored according to manufacturers instructions.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.