


arbomeric mp20

Description

Arbomeric MP20 is a one part high modulus modified polymer sealant which cures on exposure to moisture vapour to form a tough but elastic rubber.



FLOOR JOINTS

Main applications

Arbomeric MP 20 is recommended for use in many forms of construction including structural joints in heavy cladding, structural movement joints in floors and floor joints in heavily trafficked areas. NB Not recommended for joints in lightweight cladding and swimming pools.

specification compliance

BS EN ISO 11600 – F – 25 HM

application instructions

Joint preparation

The joint surfaces must be clean, dry and free from all contamination. The surfaces should be degreased using the appropriate Arbo Cleaner. Primers may be required on some substrates. It is recommended that Adshead Ratcliffe Technical Services Department should be consulted and advice obtained with regard to the choice of primer for specific purposes.

Joint Backing

Where applicable, appropriate joint filler e.g. closed cell polyethylene foam, should be used to provide the correct joint depth.

All joint preparation, priming, and sealant application should be carried out in accordance with BS 8000 Part 16, the British Standard for the sealing of joints in buildings using sealants.

application

Arbomeric MP20 is supplied in polyethylene 380ml cartridges and 600 ml foils

Joint Size Suitability

Joint Width

Minimum 6mm

Maximum 25mm (single application); 35mm (multiple applications)

Joint Depth

Minimum 10mm on porous substrates (12mm in floor joints)

Minimum 6mm on non-porous substrates (12mm in floor joints)

Maximum 20mm

Width: Depth ratio (within above min/max restrictions)

2:1 butt joints

1:1 lap joints/floor joints

packaging

25 x 380ml Polyethylene Cartridges per box. Polyethylene Nozzles are included in each box.

colours

White, Grey, Black.

storage life

12 months in original unopened packaging stored in a cool, dry place out of direct sunlight.

Health and safety

No particular health hazards are associated with this product but please consult Material Safety Data Sheet for full information.

technical Data

Skin Time at 20° C/65 % RH: 15 minutes

Application Temperature: + 5° C to + 35° C

Service Temperature: - 40° C to + 120° C

Typical Shore A Hardness: 55

Cure Rate at 20° C/65 % RH: 2mm/24 hours

Chemical Resistance: Resistant to most dilute acids and alkalis. Organic solvents may cause the sealant to swell and lose adhesion. Strong cleaning agents can cause surface deterioration and may affect the efficiency of the material.

UV Resistance: Very Good

Service Life: 20 years + (when used in trafficked areas the life may be reduced)

Movement Accommodation: Butt joints (movement in tension and compression): 35 %.

Lap joints (movement in shear): 70 %.

Modulus @ 100 % extension: 1.12 N/mm²

Ultimate elongation: 220%

Tensile strength @ break: 1.85 N/mm²

accessories**Primers**

Arbo Primer 2650 (500ml tin):

Yield approximately 125 metres per tin

Cleaners

Arbo Cleaner No.17- 1 Litre Tin (Xylene based – not suitable for use with plastics or delicate finishes)

Arbo Cleaner No. 16 - 1 Litre Tin (Alcohol Based)

Ancillary Equipment

Polyethylene Nozzles

Arbo Caulking Guns

Quantity estimator

Joint Size (mm)	Metres/Litre
6 x 6	27.8
9 x 6	18.5
12 x 9	9.3
18 x 10	5.6
25 x 10	4.0

Important: The information in this leaflet is given in good faith and based on results gained from experience and tests. However, all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control. Goods are supplied subject to the Company's terms and conditions of sales, a copy of which is available on request.

Arbo sealants are manufactured in the U.K. by Adshead Ratcliffe.