

TECHNICAL DATA SHEET NO: OPTIPROOF1 VERSION: 2-18/1/11 PAGE: 1 OF 2 DATE OF ISSUE: 18/1/11

EVERBUILD OPTIMIX INTEGRAL WATERPROOFER



Colour	Product Code	Pack Size	Box Qty
Yellow	OPTIPROOF1	1ltr	10

Product Description

OPTI-MIX INTEGRAL WATERPROOFER is a highly concentrated waterproofing and air entraining admixture for sand and cement which is 25 times the strength of conventional products.

OPTI-MIX INTEGRAL WATERPROOFER forms extremely stable air bubbles in sand/cement mixes. This improves the workability of mortar/render giving it a "buttery" consistency and helps prevent shrinkage, cracking, crazing and mild frost damage during the curing process, as well as providing long term resistance to freeze/thaw cycles

It also contains pore blocking additives to reduce water absorption and reduces the chance of efflorescence (salt formation). OPTI-MIX INTEGRAL WATERPROOFER extends open time to enable large areas to be covered in one go. This product is fully tested to the requirements of EN934 Part 3 Table 2.

Benefits

- Concentrated formula 1ltr = 25ltrs of standard waterproofer.
- Easy to use gauged bottle.
- Improves water resistance of mortars.
- Added plasticising agent improves workability
- Provides resistance to freeze/thaw cycling.
- · Reduces bleeding.

Areas For Use

Pool and tank linings External renders. External pointing. Structures below ground level.

Limitations

- Do not exceed recommended dosage rate range and DO NOT overmix.
- Ensure container is always kept in a secure upright position during both storage and transit.
- Air entraining formulation not intended for structural concrete.
- Selection of correct materials and mix design relative to the substrate and exposure levels are of paramount importance.
- Materials for External Render systems and application methods should be in line with BS5262 1991 "Code of Practice for External Rendering" and BS8000 Part 10 1995 "Code of Practice for Plastering and Rendering".



TECHNICAL DATA SHEET NO: OPTIPROOF1 VERSION: 2-18/1/11 PAGE: 2 OF 2 DATE OF ISSUE: 18/1/11

• Dispose of this product and packaging correctly. Do not allow to enter watercourses. Always read label before use and wear suitable protective equipment.

• It is the user's responsibility to determine suitability for use. If in doubt, please contact Technical Services Department for further advice.

Application

Shake bottle well before use. Push the lid downwards and twist anti-clockwise to remove. Squeeze the sides of the bottle to fill the measuring cup to the required dose (20-40ml per 50kg of cement). Add Optimix Integral Waterproofer to a 10 bucket of water and stir/mix well. Dry mix all other ingredients and add sufficient quantities of water/Optimix Integral Waterproofer solution until the desired consistency is achieved. Never add this product directly to the dry mix, always let down into a portion of gauging water. Replace cap after use.

Specific Data

opecine bata		
Appearance	Semi Viscous Yellow liquid	
Specific Gravity @ 20°C	1.08	
Viscosity (Brookfield s70	1000-3000cps	
@100 rpm)		
Usage	20-40ml per 50kg of cement	
рН	11-13	

Health & Safety

Consult MSDS for full list of hazards

Storage

Store in original unopened containers between 5 and 40° C.

Shelf Life

12 months from date of manufacture.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.