

EVERBUILD QUICKMAC



Colour	Product Code	Pack Size	Box Qty
Black	QMAC25	25KG	1

Product Description

EVERBUILD QUICK MAC is a high specification tarmacadam repair compound designed to instantly and permanently repair roads, drives and footpaths. EVERBUILD QUICK MAC may also be used for remedial repairs around roadside ironwork (e.g. manholes).

Benefits

- Ready to use cold lay product – just fill and compact down.
- Instantly trafficable
- Will not displace – stays where it is put

Areas for Use

- Repairing tarmac roads, driveways etc.
- Repairing tarmac footpaths.
- Remedial work around ironworks i.e. drains, manhole covers etc.

Limitations

- Do not use in a wearing course at less than 20mm depth.
- As the manufacturer cannot know all the uses its products may be put to, it is the users responsibility to determine suitability for use. If in doubt, contact technical services department for advice or refer to technical data sheet

Surface Preparation

Correct preparation is the key to maximum durability. Suitable for application where minimum depth is 20mm to 60mm maximum. Compact base with suitable aggregate to required depth below wearing course, and sweep clean of dirt or loose debris. Apply EVERBUILD COLD JOINT SEALER to any clean cut vertical surfaces.

Application

- **High traffic public areas:** (carriageways, footpaths, cycle tracks, tennis courts etc) For maximum durability a 60mm wearing course is recommended. Apply QUICK MAC into recess and rake to a depth of 45mm (ie 50% greater than compacted depth). Compact to 30mm in accordance with Appendix 8 of the Re-Instatement of Openings in Highways 1992. Re-seal vertical surfaces with EVERBUILD COLD JOINT SEALER, re apply and rake to 45mm, and compact as above back to 30mm level with the existing surface.

- **Low traffic domestic areas:** (eg driveways, garden paths) – prepare, compact base and prime vertical surfaces in same way as above, but lesser depths of QUICKMAC may be used if required. Holes are filled to 50% greater than their depth and compacted level. NOTE: do not use as a final wearing course at less than 20mm in compacted depth.

Health & Safety

Consult MSDS for full list of hazards.

Storage

Store in cool dry conditions between + 5°C and 25°C. Storage outside these parameters will significantly reduce shelf life.

Shelf Life

6 months in original unopened bag. This will reduce significantly once opened.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.