

Silirub Cleanroom

Revision: 13/03/2014

Page 1 from 2

Technical data

Basis	Polysiloxane
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (20°C / 65% R.H.)	Ca. 30 min
Curing speed * (20°C / 65% R.H.)	Ca. 2 mm/24h
Hardness	20 ± 5 Shore A
Density	1,36 g/ml
Elastic recovery (ISO 7389)	> 80 %
Maximum allowed distortion	25 %
Temperature resistance	-50 °C → 120 °C
Max. tension (DIN 53504)	2,10 N/mm ²
Elasticity modulus 100% (DIN 53504)	0,30 N/mm ²
Elongation at break (DIN 53504)	> 1200 %
Application temperature	5 °C → 35 °C



(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

Product description

Silirub Cleanroom is a high-quality, neutral, elastic one-component silicone based joint sealant. Silirub Cleanroom has been developed for sealing applications in critical surroundings (hospitals, laboratories, pharmaceutical industry) and in foodsafe applications.

Properties

- Very easy to apply
- Colourfast and UV resistant
- Impervious to mould, contains ZnP and Carbendazym (biocides with fungicidal action)
- Permanent elastic after curing
- Very good adhesion on many materials
- Meets GEV EMI CODE EC1 PLUS: very low emission
- Low modulus
- Slow skinning time
- Tested according to FDA regulations code CFR 21 § 177.2600 (e) and (f)

Applications

- Sealing in cleanroom applications in hospitals, laboratories and other critical surroundings.
- Sealing of rooms in which food is processed and stored.
- Sealing of several panel types (like e.g. HPL-panels).
- Joints in sanitary rooms (on synthetic baths and tubs) and kitchens.

Packaging

Colour: white

Packaging: 310 ml cartridge

Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C. Important: This product is heat sensitive. Storage and transport in warm conditions will reduce the shelf life to 6 months.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.



Silirub Cleanroom

Revision: 13/03/2014

Page 2 from 2

Substrates

Substrates: all usual building substrates

Nature: clean, dry, free of dust and grease.

Surface preparation: Porous surfaces in water loaded applications should be primed with Primer 150. All smooth surfaces can be treated with Surface Activator. We recommend a preliminary adhesion test on every surface. There is no adhesion on PE, PP, PTFE (Teflon®), silicones and bituminous substrates. We recommend a preliminary compatibility test.

Max. width for joints: 30 mm

Min. depth for joints: 5 mm Recommendation sealing jobs: joint width = 2 x joint depth.

Application method

Application method: With manual- or pneumatic caulking gun. *Cleaning:* Clean with white spirit or Surface Cleaner immediately after use. *Finishing:* With a soapy solution or Soudal Finishing Solution before skinning. *Repair:* With the same material

Joint dimensions

Min. width for joints: 5 mm

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

Remarks

- Do not use on natural stones like marble, granite,...(staining). Use Soudal Silirub MA for this application.
- Direct contact with the primary sealing of double glazing units (insulation) and the PVB-film of safety glass must be avoided.
- The sanitary formula should not replace regular cleaning of the joint. Excessive contamination, deposits or soap remainings will stimulate the development of fungi.

Standards

- IKI (institute für Krankenhaushygiene, Giessen, Germany) approvals for Desinfection and barrier against microorganisms (on Trespa Meteon panels). □ FDA code 21 §177.2600 (e): tests by IANESCO (France), report 10225 dated 31 October 2002
- IFT-ROSENHEIM® conform DIN EN ISO 11600 F 25 LM

Environmental clauses *Leed*

regulation:

Complies with USGBC LEED® 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

