# Soudaseal MS Clear

Revision: 13/03/2014 Page 1 from 2

### **Technical data**

Basis	MS Polymer
Consistancy	Stable paste
Curing system	Moisture curing
Skin formation* (20°C / 65% R.H.)	Ca. 10 min
Curing speed * (20°C / 65% R.H.)	2 mm/24h → 3 mm/24h
Hardness	38 ± 5 Shore A
Density	1,04 g/ml
Elastic recovery (ISO 7389)	> 75 %
Maximum allowed distortion	± 20 %
Temperature resistance	-40 °C → 90 °C
Max. tension (DIN 53504)	2,40 N/mm²
Elasticity modulus 100% (DIN 53504)	0,80 N/mm²
Elongation at break (DIN 53504)	300 %
Application temperature	$5 ^{\circ}\text{C} \rightarrow 35 ^{\circ}\text{C}$



recillical Data Sile

(\*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

#### **Product description**

Soudaseal MS Clear is a high quality, crystal clear, neutral, elastic, 1-component adhesive based on MS-Polymer.

#### **Properties**

- crystal clear formulation
- Excellent adhesion on nearly all surfaces, even if slightly moist.
- Very good mechanical characteristics.
- Good extrudability even at low temperatures
- Ecological advantages free of isocyanates, solvents, halogens and acids
- Can be painted with all water based paints and many other systems (to be tested)
- · Permanent elastic after curing

#### **Applications**

- All common bonding and sealing applications, both in and outdoor.
- Transparent and elastic bonding in construction and building applications.
- Invisible bonding of glass and other transparent materials in indoor applications.

#### **Packaging**

Colour: transparent Packaging: 290 ml cartridge

#### Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

#### **Chemical resistance**

Good resistance to water, aliphatic solvents, hydrocarbons, ketones, esters, alcohols, diluted mineral acids and alkalis and (salt) water. Poor resistance to aromatic solvents, concentrated acids and chlorinated hydrocarbons.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.





Page 2 from 2

## Soudaseal MS Clear

Revision: 13/03/2014

**Substrates** 

Substrates: all usual building substrates, glass, treated wood, PVC, plastics, metals, stone, concrete, ...

Nature: clean, free of dust and grease. Surface preparation: Porous surfaces in water loaded applications should be primed with Primer 150. All smooth surfaces can be treated with Surface Activator.

While producing plastics very often releasing agents, processing aids and other protective

no adhesion on PE, PP, PTFE (Teflon®), silicones and bituminous substrates. NOTICE: bonding plastics like PMMA (e.g. Plexi® glass), polycarbonate (e.g. Makrolon® or Lexan®) in stress loaded applications can give rise to stress cracking and crazing in these substrates. The use of Soudaseal MS Clear is not recommended in these applications.

Joint dimensions

Min. width for bonding: 1 mm

agents (like protection foil) are used. These should be removed prior to bonding. There is

Min. width for joints: 5 mm
Max. width for bonding: 3 mm

Max. width for joints: 10 mm Min. depth for joints: 5 mm

#### **Application method**

Application method: With manual- or pneumatic caulking gun. Cleaning: With Fix ALL Cleaner immediately after use. Cured Soudaseal MS Clear can only be removed mechanically. Finishing: With a soapy solution or Soudal Finishing Solution before skinning. Repair. With the same material

#### **Health- and Safety Recommendations**

Take the usual labour hygiene into account. Consult label for more information.

#### **Remarks**

- Soudaseal MS Clear is paintable with waterbased paints, however due to the large number of paints and varnishes available we strongly suggest a compatibility test before appication.
- The drying time of alkyd resin based paints may increase.
- Soudaseal MS Clear can be applied to a wide variety of substrates. Due to the fact that specific substrates such as plastics, like polycarbonate, etc, may differ from

- manufacturer to manufacturer, we recommend preliminary compatibility test.
- Soudaseal MS Clear is not suitable for expansion joints.
- Do not use in applications where continuous water immersion is possible. □
   Not suitable for sanitary applications.
- Soudaseal MS Clear has a good UV resistance but can discolour under ewtreme conditions or after very long UV exposure.
- Soudaseal MS Clear can not be used as a glazing sealant.
- Soudaseal MS Clear cannot be used on natural stone. Because the adhesion surface will discolour under influence of the sealant (looks wet) and because this is visible through the crystal clear sealant it seems like staining has occurred.

Environmental clauses Leed regulation:
Soudaseal MS Clear conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED® 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOCcontent.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Soudal NV Everdongenlaan 18 - 20 BE-2300 Turnhout Tel: +32 (0)14-42.42.31 Fax: +32 (0)14-42.65.14 www.soudal.com