

## TARMAC RESTORER



Colour	Product Code	Pack Size	Box Qty
Black	TARR25	25Ltr	1
	TARR5	5Ltr	4

### Description and Uses

Everbuild Tarmac Restorer is a high performance surface coating specially formulated to make existing tarmac look like new. Once dry Everbuild Tarmac Restorer provides a tough, durable, low sheen finish which protects from weathering, oil and petrol spills and unsightly plant/weed growth. The quick drying formula enables driveways to be used after only 4 hours.

### Benefits

- Tough and long lasting
- Protects against common spills and plant / weed growth
- Fast drying.

### Areas For Use

Tarmac drives

### Limitations

- Do not use if ambient air or surface temperature is below 5 °C.
- Do not use if rain is imminent (within 6 hours).
- Do not use over fresh tarmac. Allow Tarmac to dry for a minimum of 3 months prior to application.
- Do not subject to vehicular traffic within 4 hours of application.
- At lower temperatures drying times will be significantly extended. Always check surface is dry before trafficking.
- Oil, petrol or chemical spills should be removed from Tarmac Restorer as quickly as possible with warm water, detergent and a clean cloth.
- Do not use a high pressure spray to clean Tarmac Restorer.
- It is the user's responsibility to determine suitability for use. If in any doubt contact Technical Services for advice.

### Surface Preparation

All surfaces must be clean and free from any loose dirt or debris. The surface may be damp however any surface water/puddles must be removed. Use Everbuild Oil Away to remove any oil or grease spills. Lichen or surface mould can be removed using Everbuild Fungicidal Wash and cleaned using fresh water and a stiff bristled brush. Surface imperfections should be repaired using Everbuild Quick Mac or suitable repair compound.

### Application

**Always read instructions prior to use.** Stir well before and periodically during use. Apply with a brush or long pile roller in an even coat across the entire surface. Apply in 2 coats allowing 4 hours between coats. Clean all equipment immediately after use with clean water and detergent.

### Specific Data

Type Of Solvent	Water
Specific Gravity @ 20°C	0.9 – 1.1
Viscosity @ 20°C	400 - 700cPs
Coverage	4 – 6m <sup>2</sup> per litre depending on porosity of substrate
Drying Time	4-6 hours depending on drying conditions
Service Temps	-20 to +50°C
Application Temps	5-35°C. Surfaces must be free from ice and water
Film Thickness Per Coat @ 11m <sup>2</sup> / Ltr	Wet – 0.1mm Dry – 0.05mm
Chemical And Water Resistance	Resistant to: most salt solutions, dilute acids and alkalis, water and limited oil. Not resistant to: solvents and some detergent solutions

### Health & Safety

Consult MSDS for full list of hazards.

### Storage

Store in original containers in cool dry conditions above 5°C. Do not allow to freeze.

### Shelf Life

12 months from date of manufacture.

*The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.*