

## EVERFLEX WEATHER MATE SEALANT



Colour	Product Code	Pack Size	Box Qty
White	WEAWE	C3	25
Translucent	WEATR	C3	25
Black	WEABK	C3	25

### Product Description

EVERFLEX WEATHER MATE SEALANT is a multi-use sealant that can be applied in wet weather and to wet surfaces, remaining permanently flexible. Intended for external use only it can be overpainted with most paints and woodstains when cured. Adheres to most common surfaces.

### Benefits

- Can be applied in all weathers.
- Sticks to wet surfaces.
- Resists all weather conditions.
- Permanently flexible.
- Overpaintable.
- Can be used in conjunction with Bitumen and asphalt.

### Areas For Use

- For all roofline applications. Ideal for use with lead, bitumen and galvanised steel, and for sealing around flashing, gutters, downpipes and corrugated roofing.
- Ideal for perimeter pointing to all window and door frames, and all external weathersealing applications.
- For sealing between metal and composite roof and wall panels.
- For remedial sealing over all other sealant, old putties, mastics and industrial metal panel sealing.

### Limitations

- Not for use in aquarium manufacture.
- Not for internal use.
- Not for use in food preparation areas.
- Not for use on joints likely to exceed 25% movement.
- Paintable only when cured.

### Surface Preparation

All surfaces must be clean and dust free. All loose or flaking surface coatings should be removed before application. Glass, metal and aluminium should be cleaned with a proprietary solvent cleaner prior to application for optimum adhesion.

### Application

Cut the tip of the cartridge taking care not to damage the thread. Apply nozzle and cut cleanly at an angle of 45° with an opening slightly larger than the gap to be sealed. Apply using a standard sealant gun. Best results will be obtained by keeping an even pressure on the gun trigger and keeping the gun at a constant angle to the surface being sealed. Always tool down immediately following application using a spatula or piece of wood wetted with a soap and water solution. When applied to wet surfaces tooling down is essential to ensure a proper bond with the surface is formed. The product is tack free after 10-15 minutes, and should be allowed to cure for 24 hours before painting. Clean tools with white spirits.

### Specific Data

<b>Movement Accommodation</b>	+ or -25%
<b>Skinning Time</b>	15 mins @ 20°C
<b>Cure Time</b>	2mm per 24 hours
<b>Hardness Shore A</b>	22
<b>Shrinkage</b>	10%
<b>Service Temperature Resistance</b>	-25°C to + 95°C
<b>Application Temperature Resistance</b>	+5°C to + 50°C
<b>Specific Gravity</b>	1.69
<b>Cleaning</b>	Uncured sealant white spirit
<b>Minimum Joint Width</b>	5mm
<b>Maximum Joint Width</b>	35mm
<b>Joint Ratio</b>	Maximum depth 50% of joint width
<b>Elongation At Break</b>	350%

### Health & Safety

Consult MSDS for full list of hazards

### Storage

Store in cool dry conditions with good ventilation and away from sources of ignition.

### Shelf Life

Use within two years.

*The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.*